

COM 3 EAR

1. TYPICAL PROPERTIES

Total Solid Content (%)	-	60.5
Alkalinity (%)	-	0.62
MST @ 55% TSC (sec.)	-	1100
Coagulum Content (ppm)	-	20
B/F Viscosity, 2/60 at 26±2 °C (cps)	-	70
pH	-	10.70

2. TYPICAL DIPPED FILM PROPERTIES

(FILM THICKNESS 0.15 – 0.18mm TESTED IN ACCORDANCE WITH ASTM TEST METHODS)

UNAGED (ASTMD412:1992)

Modulus at 700% Elongation (MPa)	9.0
Tensile Strength (MPa)	28.0
Elongation at Break (%)	950

AGED (22hrs at 100°C)–(ASTMD573:1988)

Modulus at 700% Elongation (MPa)	7.0
Tensile Strength (MPa)	30.0
Elongation at Break (%)	1000