

# UL T

## 1. TYPICAL PROPERTIES

Total Solid Content (%)	-	60.0
Alkalinity (%)	-	0.65
MST @ 55% TSC (sec.)	-	1000
Coagulum Content (ppm)	-	20
B/F Viscosity, 2/60 at 26±2 °C (cps)	-	80
pH	-	10.50

## 2. TYPICAL DIPPED FILM PROPERTIES

*(FILM THICKNESS 0.15 – 0.18mm TESTED IN ACCORDANCE WITH ASTM TEST METHODS)*

### UNAGED (ASTMD412:1992)

Modulus at 700% Elongation (MPa)	19.0
Tensile Strength (MPa)	26.0
Elongation at Break (%)	800

### AGED (22hrs at 100°C)–(ASTMD573:1988)

Modulus at 700% Elongation (MPa)	15.0
Tensile Strength (MPa)	28.0
Elongation at Break (%)	900