

VUL N B/F

1. TYPICAL PROPERTIES

Total Solid Content (%)	-	59.80
Alkalinity (%)	-	0.35
MST @ 55% TSC (sec.)	-	1800
B/F Viscosity, 2/60 at 26±2 °C (cps)	-	70
pH	-	10.50

2. TYPICAL DIPPED FILM PROPERTIES

(FILM THICKNESS 0.15 – 0.18mm TESTED IN ACCORDANCE WITH ASTM TEST METHODS)

UNAGED (ASTMD412:1992)

Modulus at 700% Elongation (MPa)	19.0
Tensile Strength (MPa)	28.0
Elongation at Break (%)	780

AGED (7 days at 70°C)–(ASTMD573:1988)

Modulus at 700% Elongation (MPa)	16.0
Tensile Strength (MPa)	33.0
Elongation at Break (%)	850