

COM 14

1. TYPICAL PROPERTIES

Total Solid Content (%)	-	60.5
Alkalinity (%)	-	0.62
MST @ 55% TSC (sec.)	-	1300
pH	-	10.70

2. TYPICAL DIPPED FILM PROPERTIES

(FILM THICKNESS 0.15 – 0.18mm TESTED IN ACCORDANCE WITH ASTM TEST METHODS)

UNAGED (ASTMD412:1992)

Modulus at 700% Elongation (MPa)	12.0
Tensile Strength (MPa)	26.0
Elongation at Break (%)	850

AGED (22hrs at 100°C)–(ASTMD573:1988)

Modulus at 700% Elongation (MPa)	7.0
Tensile Strength (MPa)	28.0
Elongation at Break (%)	900